

Epoxy地床系列產品

建築類系列產品

防蝕系列產品

產品編號：KL-201

■ 油性導電底塗

Solvent-base Conductive Epoxy Resin Primer

- KL-201 是由特殊溶劑型環氧樹脂及硬化劑胺Amine變性合成之抗靜電環氧樹脂，耐水性及耐藥品性優良。
- KL201 is Solvent-base Conductive Epoxy Resin Floor Coating compound by special solvent-based epoxy resin and special Amine of hardener. Perfect water resistance and chemical resistance, so it is most suitably used for solvent-base coating material.

用 途USAGE

- 要求防止靜電干擾之環境 ●軍火庫、化學工廠等 ●精密電子廠、電腦中心、無塵室、醫院手術房等。
- Antistatic required area. ●Ammunition factory、Chemical factory.
- Fine electronic industries, computer center, clean room, and operation room of hospital.

特性

- 耐磨性優良。
- 導電性優異。
- 耐水性，耐酸鹼性優良。

CHARACTERISTICS

- Good wear resistance.
- Good electric conduction.
- Excellent water-resistance, acid-resistance and alkali resistance.

技術資料

Technical data

顏色:	主劑:黑色	硬化劑:黑色	Color	Resin: black	Hardener : black
配合比:	1:1		Mixing ratio	1:1	
包裝量 主劑(kg)	10		Packaging Resin(kg)	10	
硬化劑(kg)	10		Hardener (kg)	10	
可使用時間(min)	40 (25°C)		Pot life (min)	40(25°C)	
硬化時間(hr):	8 (25°C)	導電係數:10 ⁴ Ω	Full Hard (hr)	8(25°C)	dielectrics constant : 10 ⁴ Ω

產品編號：KL-202 ■ 水性導電底塗

Water-Base Conductive Epoxy Resin Primer.

- KL-202 是由特殊水性環氧樹脂及硬化劑胺Amine變性合成之抗靜電環氧樹脂，耐水性及耐藥品性優良。
- KL-202 is water-based conductive Epoxy resin compound by special water-based epoxy resin and special Amine of hardener. Perfect water resistance and chemical resistance, so it is most suitably used for water-base coating material.

用 途USAGE

- 要求防止靜電干擾之環境 ●軍火庫、化學工廠等 ●精密電子廠、電腦中心、無塵室、醫院手術房等
- Antistatic required area. ●Ammunition storage、Chemical factory.
- Fine electronic industries, computer center, clean room, ,and operation room of hospital.

特性

- 與水易於混合無溶劑之公害,符合環保需求。
- 耐水性，耐酸鹼性優良。
- 導電性優異。
- 耐磨性優良。

CHARACTERISTICS

- Easy to mixed with water, and no pollution of solvent-free
- Perfect water-resistance, acid-resistance and alkali resistance.
- Good electric conduction.
- Good wear resistance.

技術資料

Technical data

顏色:	主劑:透明液體	硬化劑:黑色	Color	Resin:Clear	Hardener : black
配合比:	1:4		Mixing ratio	1:4	
包裝量 主劑(kg)	4		Packaging Resin(kg)	4	
硬化劑(kg)	16		Hardener (kg)	16	
可使用時間(min)	30 (25°C)		Pot life (min)	30(25°C)	
硬化時間(hr):	24 (25°C)	導電係數: 10 ⁴ Ω	Full Hard (hr)	24(25°C)	dielectrics constant : 10 ⁴ Ω