

Epoxy地床系列產品

建築類系列產品

防蝕系列產品

## 產品編號：KL-203

## ■ 水性防潮底漆

## Water-Base Epoxy Anti-humidity Primer

●KL-203是水性環氧樹脂，搭配特殊氨硬化劑，可以直接加水混合，易於塗刷。其硬化後，物性佳，對潮濕面接  
著效果佳，可適用於混凝土水泥面之底漆。●KL-203 is water-base Epoxy resin, and can mixed with water, it is easy to use.

Excellent physical property of surface coating, it can be use for concrete cement and on damp or wet surface.

## 用 途 APPLICATION

●潮濕面水泥地面之底漆塗裝 ●食品廠、電子廠、GMP藥廠、無塵室、倉庫、保養場、學校、停車場、機械廠、五金工廠  
、醫院、大賣場、大樓地下室工程及潮濕面等地面塗裝。●Damp surface cement ground material, this primer is good for wet Concrete  
surface. ●Food-stuff factory, Electronic factory, GMP pharmaceutical factory, Dust-free room, warehouses, service factory, school, parking area, machine  
processing plants, metal works, hospital, underground, supermarket on floor coating.

## 特性

- 與水易於混合無溶劑之公害。
- 耐水性優異。
- 漆膜堅韌、附著性優良。
- 低敏感性，無刺激味道。

## CHARACTERISTICS

- Easy to mixed with water, and no pollution of solvent-free.
- Excellent water resistance.
- A tough film, with good adhesion.
- Low sensitivity, no excite odor.

## 技術資料

## Technical data

顏 色	主劑:透明	硬化劑:白色乳液	Color	Base :Clear	Hardener : white
配合比	1 : 4		Mixing ratio	1:4	
包裝量 主劑(kg)	4		Packaging Resin(kg)	4	
硬化劑(kg)	16		Hardener (kg)	16	
可使用時間(min)	30 (25°C)		Pot life (min)	30(25°C)	
硬化時間(hr)	24 (25°C)		Full Hard (hr)	24(25°C)	

## 產品編號：KL-223 ■ 水性防潮砂漿中塗 Water-Based Damp-proof Epoxy Intermediate Coat

●KL-223由特殊環氧樹脂 (Epoxy Resin) 及硬化劑配以耐化學性骨材精製而成之兩液－粉型水性環氧樹脂砂漿中塗漆。

● KL-223 is two package water-based powder type intermediate coat containing chemical-resisting compound.

## 用 途 APPLICATION

●食品廠、電子廠、GMP藥廠、無塵室、倉庫、保養場、學校、停車場、機械廠、五金工廠、醫院、大賣場、  
大樓地下室等地坪工程之地面塗裝。●Damp surface and Concrete cement surface。  
● Floor coating for cement structure such as foodstuff factory, electronics factory, GMP pharmaceutical factory, cleanroom, warehouse, automobile repair  
shop, school, parking lot, machinery plant, hospital, hypermarket, building underground.

## 特性

- 漆膜堅韌、附著性非常優良。
- 耐水性及耐酸鹼性佳。
- 耐機械磨損及電氣絕緣性優良
- 施工簡便，無污染。

## CHARACTERISTICS

- Tough film with good adhesion
- Excellent water, acid, alkali resistance
- Excellent wear resistance and electric insulation
- Easy to work and eco-friendly

## 技術資料

## Technical data

顏 色	主劑:透明	硬 化 劑 :微黃	Color	Base : Clear liquid	Hardener : Yellow brown liquid
配合比	1 : 2		Mixing ratio	1 : 2	
包裝量 主劑(kg)	10		Packaging Resin(kg)	10	
硬化劑(kg)	20		Hardener (kg)	20	
可使用時間(min)	20 (25°C)		Pot life (min)	20 (25°C)	
硬化時間(hr)	18 (25°C)		Full Hard (hr)	18 (25°C)	