

產品編號：KL-220 ■ 透明流展中塗

Solvent-Free Clear Spreading of Epoxy Middle Coating

- KL-220是高強度環氧樹脂，高物性、高強度，施工容易，無刺激味道，適用於地床之中塗樹脂砂漿及流展中塗。
- KL-220 is high strength non solvent Epoxy resin, easy for working, high tensile, and high physical property, suitable for middle coating of the ground, mortar resin and spreading middle coating.

用途USAGE

- 食品廠、電子廠、GMP藥廠、無塵室、倉庫、保養場、學校、停車場、機械廠、五金工廠、醫院、大賣場、大樓地下室等地坪工程之塗裝。
- Food-stuff factory、Electronic factory、GMP pharmaceutical factory、Dust-free room、warehouses、service factory、school、parking area、machine processing plants、metal works、hospital、supermarket、underground on floor coatings.

特性

- 耐酸鹼、耐溶劑性等優異。
- 接著性優異，不龜裂、不剝落。
- 耐磨耗性優異。

CHARACTERISTICS

- Excellent acid, alkali resistance and solvent resistance .
- Excellent adhesion for cement, non cracking and non peel.
- Excellent wear resistance.

技術資料

Technical data

| | | | | | |
|------------|----------|--------|---------------------|-------------|------------------|
| 顏色 | 主劑:透明 | 硬化劑:褐色 | Color | Resin:Clear | Hardener : Brown |
| 配合比 | 2:1 | | Mixing ratio | 2 : 1 | |
| 包裝量 主劑(kg) | 20 | | Packaging Resin(kg) | 20 | |
| 硬化劑(kg) | 10 | | Hardener (kg) | 10 | |
| 可使用時間(min) | 20(25°C) | | Pot life (min) | 20(25°C) | |
| 硬化時間(hr) | 8(25°C) | | Full Hard (hr) | 8(25°C) | |

產品編號：KL-222 ■ 有色流展砂漿中塗

Solvent-Free Colorful Spreading of Epoxy Middle Coating

- KL-222是高強度環氧樹脂，高物性強度，施工容易，適用於地床之流展中塗。
- KL-222 is high tensile solvent-free Epoxy resin, easy for working, has high physical strength, suitable for middle coating of the ground, mortar resin and spreading middle coatings.

用途USAGE

- 食品廠、電子廠、GMP藥廠、無塵室、倉庫、保養場、學校、停車場、機械廠、五金工廠、醫院、大賣場、大樓地下室等地坪工程之塗裝。
- Food-stuff factory, Electronic factory, GMP pharmaceutical factory, Dust-free room, warehouses, service factory, school, parking area, machine processing plants, metal works, hospital, supermarket、underground on floor coating.

特性

- 耐酸鹼、耐溶劑性等優異。
- 接著性優異，不龜裂、不剝落。
- 耐磨耗性優異。

CHARACTERISTICS

- Excellent acid, alkali resistance and solvent resistance .
- Excellent adhesion for cement surface, non cracking and non peel.
- Excellent wear resistance.

技術資料

Technical data

| | | | | | |
|------------|----------|--------|---------------------|-----------------------------|------------------|
| 顏色 | 主劑:各色 | 硬化劑:褐色 | Color | Resin: Various colored menu | Hardener : Brown |
| 配合比 | 4:1 | | Mixing ratio | 4 : 1 | |
| 包裝量 主劑(kg) | 20 | | Packaging Resin(kg) | 20 | |
| 硬化劑(kg) | 5 | | Hardener (kg) | 5 | |
| 可使用時間(min) | 20(25°C) | | Pot life (min) | 20(25°C) | |
| 硬化時間(hr) | 8(25°C) | | Full Hard (hr) | 8(25°C) | |