

Epoxy地床系列產品

建築類系列產品

防蝕系列產品

產品編號：KL-230

■ 有色流展面塗

Solvent-free Colorful Spreading of Top Coating

- KL-230係採用100%環氧樹脂，搭配特殊硬化劑精製而成，其硬化物之塗膜表面光澤優異，適用於地床材料之面漆及特別要求表面光澤及裝飾之塗裝。
- KL-230 is Solvent-free Epoxy resin, and it has excellent glossy surface after hardening. It is most suitable for surface coating for ground and glossy surface coating for the decorative.

用 途USAGE

- 食品廠、電子廠、GMP藥廠、無塵室、倉庫、保養場、學校、停車場、機械廠、五金工廠、醫院、大賣場等地坪工程之塗裝。
- Food-stuff factory、Electronic factory、GMP pharmaceutical factory、Dust-free room、warehouses、service factory、school、parking area、machine processing plants、metal works、hospital、supermarket floor coatings.

特性

- 耐酸鹼耐溶劑等優異。
- 接著性優異、不龜裂、不剝落。
- 硬度高、耐磨耗性優異。

CHARACTERISTICS

- Excellent acid, alkali resistance and solvent resistance.
- Excellent adhesion for cement, non-creasing and non peel.
- Higher hardness and excellent wear resistance.

技術資料

Technical data

顏色	主劑:各色	硬化劑:透明	Color	Resin: Various colored menu	Hardener : clear
配合比	4 : 1		Mixing ratio	4 : 1	
包裝量 主劑(kg)	20		Packaging Resin(kg)	20	
硬化劑(kg)	5		Hardener (kg)	5	
可使用時間(min)	20(25°C)		Pot life (min)	20(25°C)	
硬化時間(hr)	8(25°C)		Full Hard (hr)	8(25°C)	

產品編號：KL-231 ■ 無溶劑薄塗型面塗

Solvent-Free Epoxy Thin Top Coating

- KL-231 有色無溶劑型環氧樹脂面塗，低黏度，適合滾塗，其硬化後之塗膜表面光澤優異，流展性佳，適用於地床材料之塗裝。
- KL-231 is Solvent-free Epoxy resin, low viscosity, easy for rolling coating, and it has excellent glossy surface after hardening. It is most suitable for ground surface coatings.

用 途USAGE

- 食品廠、電子廠、GMP藥廠、無塵室、倉庫、保養場、學校、停車場、機械廠、五金工廠、醫院、大賣場等地坪工程之塗裝。
- Food-stuff factory, Electronic factory, GMP pharmaceutical factory, Dust-free room, warehouses, service factory, school, parking area, machine processing plants, metal works, hospital, supermarket floor coatings.

特性

- 流展性佳，適合滾塗。
- 接著性優異，不龜裂、不剝落。
- 耐磨耗性優異。

CHARACTERISTICS

- Excellent spreading quality. It is applied by roller.
- Good adhesion. non cracking and non peeling.
- Excellent wear resistance.

技術資料

Technical data

顏色	主劑:各色	硬化劑:透明	Color	Resin: Various colored menu	Hardener : clear
配合比	4:1		Mixing ratio	4 : 1	
包裝量 主劑(kg)	20		Packaging Resin(kg)	20	
硬化劑(kg)	5		Hardener (kg)	5	
可使用時間(min)	20(25°C)		Pot life (min)	20(25°C)	
硬化時間(hr)	12(25°C)		Full Hard (hr)	12(25°C)	