

- 由耐水、耐鹼性優異之水性壓克力樹脂為主要成份，配合特殊顏料及添加劑精製而成之有光型水性水泥漆。
- KL-350 is water base Acrylic resin, with excellent water-resistance and alkali-resistance for cement paint.

## 用途USAGE

- 適用於辦公大樓、觀光飯店、公共場所、醫院、店舖、住宅等室內水泥牆面之防護、裝飾用底面兩用漆。
- Interior Latex Gloss Wall Paint suitable for interior cement walls such as office block, tour hotel, public place, hospital, shop, house, etc.

## 特性

- 以水為調薄劑，無公害危險。
- 耐水、耐鹼性優良。
- 塗膜堅韌光亮。
- 乾燥迅速、作業性優良。

## CHARACTERISTICS

- Water base, non environment pollution.
- Excellent water-resistance and alkali-resistance.
- Glossy and tough film.
- Fast drying , good working ability;

## 技術資料

## Technical data

光澤度	有光。	Gloss	glossy
顏色	各色。	Color	General
粘度	80~110 K.U. (25°C)。	Viscosity	Above 80~110 K.U.(25°C)
遮蓋力	12.5 m <sup>2</sup> /L以上。	Hiding Power	Above 12.5 m <sup>2</sup> /L
重量	1.2 Kg/L以上。	Weight	Above 1.2 Kg/L
乾燥時間	指觸1/2小時以內，堅結2小時以內(在25°C相對溼度50%時)	Dry time	Set-to-touch within 1/2hrs, Dry-hard within 2 hrs; (at 25°C relative humidity 50%)
塗裝間隔	最少3小時以上。	Recoating interval	min 3 hrs
適用底漆	本產品可當底面兩用。	Suitable primer	This product can be used as base and top of dual purpose
理論塗佈量	42 m <sup>2</sup> /Gal(在濕膜90 μm (Micron)，乾膜35 μm(Micron)時)。	Theoretical coverage	42 m <sup>2</sup> /Gal wet film 90μm(Micron),dry film 35μm (Micron)
總不揮發物	50 %以上。	Total solids(by wt.)	min. 50%
調薄劑	自來水。	Thinner	water
調薄劑用量	5~20%。	Thinner (by volume)	5~20%.(depend on use tools)
貯藏安定性	正常情況下，至少一年。	Storage stability	under the normal condition, one year at least
塗裝方法	刷塗、噴塗、滾塗。	Application method	Brushing, spraying, rolling