



產品編號：KL-001

Epoxy地床系列產品

建築類系列產品

防蝕系列產品

工程紅丹底漆 Red Lead Primer

- 由醇酸樹脂及特殊樹脂配合紅丹防銹顏料精製而成之紅丹防銹底漆。

•KL-001 is an anti-corrosive paint based on alkyd and special resins with high red lead pigment.

用途 USAGE

- 金屬、橋樑、鋼鐵構造物用之防銹底漆。
- use on iron metal, bridge , steel structures ,as anti corrosive and rust of metal primer .

特性

- 防銹性能特佳。
- 耐鹽水性優良。
- 乾燥迅速、容易施工。
- 耐水性、耐油性優良。

CHARACTERISTICS

- Excellent anti-corrosive.
- Excellent salty water-resistance.
- Fast dry, easy to use.
- Water resistance and oil resistance.

技術資料

Technical data

光澤度	平光。
顏色	橙色。
粘度	80~95 K.U.(25°C)。
遮蓋力	10m²/L以上。
重量	1.3 Kg/L以上。
乾燥時間	指觸30分鐘以內，堅結4小時以內(在25°C 相對濕度50%時)。
塗裝間隔	6小時以上(25°C)。
適用面漆	KL-030快乾調合漆、KL-031調合漆。
理論塗佈量	40m²/Gal(在濕膜85 μm(micron)，乾膜45 μm(micron)時)
總不揮發物	70%以上(重量不揮發物)。
調薄劑	松香水；用量：5~10%(視使用工具而定)。
乾膜厚度	35~45 μm(噴塗一道)。
貯藏安定性	正常情況下，至少一年。
塗裝方法	刷塗、滾塗、噴塗、無氣噴塗。

Gloss	Flat
Color	Orange
Viscosity	80~95 K.U.(25°C)
Hiding power	Above 10m²/L
Weight	Above 1.3Kg/L
Dry time	Set-to-touch within 30mins, dry-hard within 4hrs;(at 25°C relative humidity 50%)
Recoating interval	min.6hrs(25°C)
Suitable top coat	KL-030 Fast dry Ready Mixed Paint, KL-031 Ready Mixed paints
Theoretical coverage	40m²/Gal wet film 85μm (Micron), Dry film 45μm(Micron)
Total solids (by wt.)	min.70%
Thinner	Red Lead Primer thinner
Thinner (by volume)	5~10% (depend on use tools)
Suggested D.F.T.	35~45μm(per coat)
Storage stability	under the normal condition,one year at least
Application method	Brushing, rolling, air-spray, airless-spray

G.W.PAINTS