

Epoxy地床系列產品

建築類系列產品

防蝕系列產品

產品編號：KL-030

## 快乾調合漆 Fast dry Ready Mixed Paint

- 由快乾型鄰苯二甲酸酐樹脂(Alkyd Resin)為主要成份，配合特殊顏料及添加劑，精製而成之各色面漆。
- KL-030 is Enamel paint based on oil alkyd resin, and weather resistance pigment. is good appearance, fast drying, and gloss retention to weathering.

### 用途USAGE

- 適用於室內及室外一般鐵材木材構造物用之面漆。
- Suitable on steel, wooden, and plywood finishing coating.

### 特性

- 耐候性優良。
- 塗膜堅韌、附着力強。
- 抗濕性、耐水性優良。
- 作業性優良、容易施工。

### CHARACTERISTICS

- Weathering resistance.
- A tough film, with good adhesion.
- Water resistance and anti-humid.
- Easy to use, good working ability.

### 技術資料

### Technical data

光澤度	80%以上。
顏色	各色。
粘度	75~90 K.U. (25°C)。
遮蓋力	12.5m <sup>2</sup> /L以上。
重量	1.1 Kg/L以上。
乾燥時間	指觸2小時以內，堅結6小時以(在25°C 相對濕度50%)
塗裝間隔	12小時以上(25°C)。
適用底漆	(1).金屬面：KL-001, KL-002系列紅丹漆。 (2).輕金屬：用KL-601伐銹底漆。
理論塗佈量	40m <sup>2</sup> /Gal(濕膜75μm(micron), 乾膜30μm(micron))。
總不揮發物	50%以上(重量不揮發物)：40%以上(體積不揮發物)。
調薄劑	松香水；用量：5~15%(視使用工具而定)。
乾膜厚度	35~40μm(噴塗一道)。
貯藏安定性	正常情況下，至少一年。
塗裝方法	刷塗、滾塗、噴塗、無氣噴塗。

Gloss	min. 80%
Color	Generally
Viscosity	75~90 K.U. (25°C)
Hiding Power	Above 12.5/m <sup>2</sup> L
Weight	Above 1.1 kg/L
Dry time	Set-to-touch within 2hrs, dry-hard within 6hrs; (at 25°C relative humidity 50%)
Recoating interval	min. 12 hrs (25°C)
Suitable Primer	Metal covering (1)KL-001, KL-002 Red lead Primer.(2)Light steel: KL-601 Wash Primer
Theoretical coverage	40m <sup>2</sup> / Gal wet film 75μm (Micron), Dry film 30μm (Micron)
Total solids	min. 50% (weight); 40% (volume)
Thinner	Fast dry Ready Mixed Paints thinner
Thinner (by volume)	5~15% (depend on use tools)
Suggested D.F.T.	35~40μm(per coat)
Storage stability	under the normal condition, one year at least
Application method	Brushing, rolling, air-spray, airless-spray

G.W. PAINTS